



合创过滤技术（杭州）有限公司
HC filtration (Hangzhou) Co., Ltd

常用精密过滤器液体滤袋数据表

PP 微米级针刺毡

材料孔径（微米）		1	5	10	25	50	75	100	200
性能指标									
克重(g/m ²)		550	400	400	400	400	320	350	400
厚度(mm)		3.5	2.5	2.2	3	3.5	3.5	3.8	3.8
透气率(L/m ² /S)		150	300	360	500	1000	2000	1500	1500
断裂强度 (N/5×20cm)	经	1000	500	500	500	500	500	500	500
	纬	1500	1000	1000	1000	700	600	500	700
断裂伸长 (%)	经	50	60	80	85	90	100	100	105
	纬	50	60	80	85	90	80	100	90

PE 微米级针刺毡

滤料孔径（微米）		1	5	10	25	50	75	100	200
性能指标									
克重(g/m ²)		550	400	400	400	400	400	400	400
厚度(mm)		3.5	2.5	2.2	2.8	3.5	3.5	3.5	3.8
透气率(L/m ² /S)		150	330	375	550	1050	1200	1500	2000
断裂强度 (N/5×20cm)	经	1000	800	800	500	500	500	500	500
	纬	1800	1000	1000	800	600	600	500	600
断裂伸长 (%)	经	50	60	60	70	100	100	100	110
	纬	50	60	70	70	80	80	100	100

注：以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference.