



合创过滤技术（杭州）有限公司
HC filtration (Hangzhou) Co., Ltd

FC-M 聚丙烯复丝滤布数据表

品名	断裂强度	经纬密度	厚度	重量	透气度	织物组织
	(N/5*20cm)	(根/10cm)	(mm)	(g/m2)	L/m2. s	
521	2608/2050	214.8/150.8	0.79	302.7	216.5	斜纹
522	2104/1633	244/173	0.41	155	73.44	平纹
534	2501/1894	193.6/100.0	0.99	368.1	41.2	平纹
4212 短纤	2672/1342	236.4/123.2	1.34	389.4	85.6	斜纹
700A	3426.6/2819.4	204/106	0.7	350	11.7	平纹
700B	4648.0/2866.6	188/114	0.59	280	254.2	斜纹
700AB	6865.4/416.7	378/235	1.15	580	13	斜纹+平纹
750A (840A)	4466/2905	168/131	0.85	330	12	平纹
750B (840B)	5234/3489.	256/141	0.99	420	76	斜纹
750AB (840AB)	6718/5421	333.8/204.4	1.36	489.9	24.5	平纹
840-1	5275/3948	252/146	0.9	440	45.5	斜纹
840-2	5928/4086	283/142	1	490	40.7	斜纹
840-3	6282/4858	311/134	1.1	520	27.2	斜纹
858	4418/3618	251/124	0.88	380	240.7	斜纹
4218	8568/5427	456/94	1.32	660	38.4	斜纹
4135	6797/2508	346/83	1.02	510	19.12	平纹
4422	2643/1514	181/94	1.18	480	17.86	斜纹
1000A	5585.7/4089.2	204/102	0.85	435	9.83	平纹
1000B	6636/1481	204/110	0.79	430	21.49	斜纹
1500-1	56283701	251118	1.42	725	29.38	斜纹
108B	8721/4642	503/133	1.1	600	13.6	两面斜纹
108C	8367/4797	504/177	1.03	600	22.96	缎纹
丙纶输送带	10398/8006	448/141	0.9	900	8.2	重平纹

注：以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference.



合创过滤技术（杭州）有限公司
HC filtration (Hangzhou) Co., Ltd

FC-M 聚酯复丝滤布数据表

品名	断裂强度	经纬密度	厚度	重量	透气度	织物组织
	(N/5*20cm)	(根/10cm)	(mm)	(g/m ²)	L/m ² . s	
60-8 (130)	1363/111.6	260.0/221.6	0.27	125.6	130.6	平纹
60-10 (240)	2508/958.0	225.6/156.0	0.42	219.47	36.1	平纹
60-9 (260)	2202/1776	205.6/160.8	0.47	257	32.4	平纹
60-7 (621)	3026/2288	191.2/134.0	0.65	342.4	37.8	平纹
5926 (120-7)	4498/4044	260/202	1.42	610	54	斜纹
734 (120-12)	2072/1633	232/166	0.62	245	480	斜纹
745 (120-13)	1936/730	232/196	0.48	210	125	平纹
747 (120-14)	2026/1485	226/158	0.53	248	120	平纹
758 (120-15)	2594/1909	194/134	0.73	330	100	平纹
3927 (120-16)	4598/3154	156/106	0.9	524	18	平纹
728 (120-17)	2753/1869	246/310	0.89	360	180	斜纹
729	3180/2157	307/201	0.72	315	120	缎纹
208	2788/1930	360/276	1.43	400	280	斜纹
822	5760/3480	260/102	1.65	940	22	斜纹

注：以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference.



合创过滤技术（杭州）有限公司
HC filtration (Hangzhou) Co., Ltd

PA 锦纶复丝滤布数据表

品名	断裂强度	经纬密度	厚度	重量	透气度	织物组织
	(N/5*20cm)	(根/10cm)	(mm)	(g/m ²)	L/m ² . s	
407	1913 /1539	240.8/187.2	0.42	195.4	29.7	平纹
663	2390 /2202	236/156	0.58	300	23	平纹
601	3410.75/ 3365	132.0/160.8	0.49	315	125	平纹
301	2016 /1981	275.0/250.0	0.22	106.8	114.4	平纹

注：以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference



合创过滤技术（杭州）有限公司
HC filtration (Hangzhou) Co., Ltd

PVA 维纶复丝滤布数据表

品名	断裂强度	经纬密度	厚度	重量	透气度	织物组织
	(N/5*20cm)	(根/10cm)	(mm)	(g/m2)	L/m2. s	
295-1A	4302.2 /2138.4	100.0/64.6	1.56	555.8	43.7	平纹
295-102	1706 / 1556	188/141	0.71	360	29	平纹
295-104	1591 / 1141	232.4/164	0.58	246.9	40.5	平纹
295-1	2410/ 2630	157/110	0.95	50.8	15	平纹

注：以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference