



合创过滤技术（杭州）有限公司

HC filtration (Hangzhou) Co., Ltd

常用压滤机滤布数据表

品名	断裂强度	经纬密度	厚度	重量	透气度	织物组织
	(N/5*20cm)	(根/10cm)	(mm)	(g/m ²)	L/m ² . s	
PE 5926 (120-7)	4498/4044	260/202	1.42	610	54	斜纹
PE 3927 (120-16)	4598/3154	156/106	0.9	524	18	平纹
PE 822	5760/3480	260/102	1.65	940	22	斜纹
PE 621	3026/2288	191.2/134.0	0.65	342.4	37.8	平纹
PP 4212 短纤	2672/1342	236.4/123.2	1.34	389.4	85.6	斜纹
PP 700AB	6865.4/416.7	378/235	1.15	580	13	斜纹+平纹
PP 750A (840A)	4466/2905	168/131	0.85	330	12	平纹
PP 750B (840B)	5234/3489.	256/141	0.99	420	76	斜纹
PP 750AB (840AB)	6718/5421	333.8/204.4	1.36	489.9	24.5	平纹
PP 858	4418/3618	251/124	0.88	380	240.7	斜纹
PP 4218	8568/5427	456/94	1.32	660	38.4	斜纹
PP 4135	6797/2508	346/83	1.02	510	19.12	平纹
PP 7010	2643/1514	181/94	1.18	480	17.86	斜纹
PP 0707	5585.7/4089.2	204/102	0.85	435	9.83	平纹
PP 8015	6636/1481	204/110	0.79	430	21.49	斜纹
PP 8016	56283701	251118	1.42	725	29.38	斜纹
PP 108B	8721/4642	503/133	1.1	600	13.6	两面斜纹
PP108c	8367/4797	504/177	1.03	600	22.96	缎纹
PA 663	2390 /2202	236/156	0.58	300	23	平纹
PVA295-1	2410/ 2630	157/110	0.95	50.8	15	平纹
PP 单丝 2815	4041/2523	556/244	0.5	330	17.5(可定制)	重斜纹
PP 单丝 2816	3715/2016	380/119	0.58	380	36.9	缎纹
PP 单丝 1684	3761/5425	449/94	0.8	455	45.3	平纹
PP 单丝 8000	4515.4/2539.4	236/630	0.66	390/	75(可定制)	斜纹（双层）
PA 单丝 8010 黑色	2668/1258.6	220/551	0.47	330	417	缎纹
PA 单丝 8910 黄色	2668/1258.6	220/551	0.47	330	417	缎纹
PA 单丝 8015	2547.47/1746	189/512	0.54	420	807.3	缎纹
PA 单丝 8016	2342.25/1763.25	212/472	0.53	370	531	人字缎纹
PA 单丝 3038	2412.7/1877.3	110/118	0.89	280	54.5	斜纹
PP 无纺布	2100/1300	/	2.5	750	100	无纺
PP 无纺布	2300/1300	/	3.0	800	200	无纺

注：以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference