



合创过滤技术（杭州）有限公司
HC filtration (Hangzhou) Co., Ltd

常用离心机滤布数据表

品名	断裂强度	经纬密度	厚度	重量	透气度	织物组织
	(N/5*20cm)	(根/10cm)	(mm)	(g/m ²)	L/m ² . s	
747 (120-14)	2026/1485	226/158	0.53	248	120	平纹
☆758 (120-15)	2594/1909	194/134	0.73	330	100	平纹
☆3927 (120-16)	4598/3154	156/106	0.9	524	18	平纹
60-10 (240)	2508/958.0	225.6/156.0	0.42	219.47	36.1	平纹
60-9 (260)	2202/1776	205.6/160.8	0.47	257	32.4	平纹
☆60-7 (621)	3026/2288	191.2/134.0	0.65	342.4	37.8	平纹
534	2501/1894	193.6/100.0	0.99	368.1	41.2	平纹
4212 短纤	2672/1342	236.4/123.2	1.34	389.4	85.6	斜纹
700A	3426.6/2819.4	204/106	0.7	350	11.7	平纹
☆750A (840A)	4466/2905	168/131	0.85	330	12	平纹
☆750B (840B)	5234/3489.	256/141	0.99	420	76	斜纹
750AB (840AB)	6718/5421	333.8/204.4	1.36	489.9	24.5	平纹
840-1	5275/3948	252/146	0.9	440	45.5	斜纹
840-2	5928/4086	283/142	1	490	40.7	斜纹
840-3	6282/4858	311/134	1.1	520	27.2	斜纹
108B	8721/4642	503/133	1.1	600	13.6	两面斜纹
☆108C	8367/4797	504/177	1.03	600	22.96	缎纹
☆PP 单丝 2815	4041/2523	556/244	0.5	330	17.5(可定制)	重斜纹
PP 单丝 2816	3715/2016	380/119	0.58	380	36.9	缎纹
PP 单丝 1684	3761/5425	449/94	0.8	455	45.3	平纹
☆PP 单丝 8000	4515.4/2539.4	236/630	0.66	390/	75(可定制)	斜纹 (双层)

注：☆离心机滤布常用规格。

以上产品技术参数为合创过滤平均测试参数，仅供参考

Above data are the averages obtained from a series of typical by HC Filter and are just for reference.